

TECHNICAL INFORMATION

POLIMAL[®]

143 AWTP-2

Application

Polimal 143 AWTP-2 is recommended for production of polyester - glass laminates.

Features

Polimal 143 AWTP-2 is accelerated, constructional, tixotropic, terephthalic, unsaturated polyester resin with colour curing indicator and low styrene emission. It has low viscosity and good strength parameters.

Typical parameteres

Parameter/Standard	Unit	Value
Viscosity at 25°C acc.to ISO 3219	mPa s	180 ÷ 230
Gel time at 25°C acc. to DIN 2535	min	20 ÷ 30
Flexural strenght acc. to ISO 178	MPa	110
Tensile strenght acc. to ISO 527	MPa	70
Tensile modulus acc. to ISO 527	MPa	3500
Elongation at breake acc. to ISO 527	%	2,5
Heat Deflection Temperature (HDT) acc. to ISO 75	°C	65
Barcoll hardness ASTM-D 2583-95	°B	42
Guarantee period	month	3

Gel time with: 1,0% Luperox[®] K-1S

Mechanical parameters refer to not reinforced resin curing for 24 hours at room temperature and post curing for 2 hours at 80°C.

Storage conditions

Polimal 143 AWTP-2 should be stored in close package in a dry, shady and cool places at temperatures not exceeding 25°C.

Processing conditions

The resin should be mixed before use. Good curing required ambient temperature above 18°C and low air humidity. It is possible to adjust gel time by varying of amount of hardener, the best within in the range of 1 – 2 %. The final curing could be optimize by postcuring at elevated temperatures. The content of styrene emission suppressant in the **Polimal 143 AWTP-2** intensifies decreasing the interlayer adhesion, therefor it is necessary to laminate so as not to leave too much resin on the laminate surface that is to be laminated again. If the stoppage in laminating is longer than 24 hours or the resin amount on the laminate is too big, it is necessary to polish (or sand blast) the laminate surface before laying down the next layer.

Polimal[®] is the trade name reserved for unsaturated polyester resins produced by **CIECH - Sarzyna S.A.**

Luperox[®] is the trade name registered for products of **ARKEMA** company.

Data and suggestions included in this document are on the basis of our own tests and are considered by us as reliable. However, we cannot take any responsibility for actions and losses directly or indirectly resulted from using our products. User should check the product quality, safety and properties before its using.

Note:

The information does not substitute Material Safety Data Sheet or Technical Specification, which are superior documents and are available on the customer's request.