

TECHNICAL INFORMATION**POLIMAL[®]****VE-2MM****Application**

Polimal VE-2MM is recommended for production of chemical resistant compositions which are reinforced with fiberglass and/or mineral fillers.

Features

Polimal VE-2MM is a medium reactive vinyl ester resin, based on epoxide. The resin is characterized by good processing properties and high thermal and chemical resistance.

Typical parameters

Tested parameter/standard	Unit	Value
Viscosity, (at 25°C) acc. to ISO 3219	mPa s	300÷400
Gel time (at 25°C) acc. To ISO 2535	min	15÷35
Tensile strength acc. to ISO 527	MPa	75
Flexural strength acc. to ISO 178	MPa	130
Tensile modulus acc. to ISO 527	MPa	3500
Elongation at break acc. to ISO 527	%	3,5
Heat deflection temperature (HDT) acc. to ISO 75	°C	95
Barcol hardness ASTM-D 2583-95	°B	35
Guarantee period	months	3

Gel time with: 0,6% Co 1% + 1,2% DMA-10 + 2% MEKP
(e.g. Luperox® K-1).

The specified mechanical properties refer to non-reinforced resin after curing for 24 hours at room temperature and post-curing for 4 hours at 80°C.

Storage conditions

The resin should be stored in closed original containers, in dry, well ventilated and shaded storage rooms adapted for storing inflammable materials at a temperature below 25°C. Prolonged storage outside of recommended conditions can influence liquid resin properties like viscosity and gel time.

Processing conditions

The resin and components must be seasoned at temperature min. 18°C at a relative humidity below 75% before using. The curing system under productions conditions should be tested.

In order providing optimal mechanical and resistance parameters is recommended to use glass veil with a grammage of 30g/m² made of C-glass as first laminate layer and post-curing at elevated temperature e.g. couple hours at 80°C. Post-curing is especially recommended if parts are intended for contact with chemicals. In disadvantageous curing conditions [low temperature, high humidity] it is better to apply the amine curing composition:

- 1–3 % of DMA-10 accelerator
- 1–3% of dibenzoyl peroxide 50% e.g. Luperox® ANS-50

It is required to mix the resin in the tank or in the unit packages before using.

Polimal[®] is the trade name reserved for unsaturated polyester resins produced by **CIECH - Sarzyna S.A.**

Luperox[®] is the trade name registered for products of **ARKEMA** company.

Data and suggestions included in this document are on the basis of our own tests and are considered by us as reliable. However, we cannot take any responsibility for actions and losses directly or indirectly resulted from using our products. User should check the product quality, safety and properties before its using.

Note:

The information does not substitute Material Safety Data Sheet or Technical Specification, which are superior documents and are available on the customer's request.

CIECH Sarzyna S.A.

ul. Chemików 1
37-310 Nowa Sarzyna
tel. (+48 17) 24 07 111
faks (+48 17) 24 07 122
sarzyna@ciechgroup.com
www.ciechgroup.com

REGON: 000042352
NIP: 8160001828

Kapitał zakładowy:
84 900 000,00 zł (wplacony w całości)

Rejestr przedsiębiorców:
Sąd Rejonowy w Rzeszowie, XII Wydział
Gospodarczy Krajowego Rejestru Sądowego
KRS: 0000103271

TECHNICAL INFORMATION

POLIMAL[®]

VE-2MM

Chemical Resistance Table

Assessment of chemical resistance of non-reinforced resin to undermentioned chemicals was carried out under laboratory conditions according to PN-78/C 89067 standard. Test specimens have seasoned for 24 hours at temperature 23°C and the for 4 hours at temperature 80°C.

Chemical	Concentration	Temperature, °C
Nitric acid	25%	50
Phosphoric acid	75%	80
Hydrochloric acid	20%	80
Hydrochloric acid	38%	45
Sulphuric acid	10%	90
Sulphuric acid	70%	75
Formic acid	25%	75
Acetic acid	15%	90
Acetic acid	25%	90
Acetic acid	50%	70
Acetic acid	80%	45
Aqueous ammonia	25%	25
Hydrogen peroxide	30%	40
Sodium hydroxide	1%	65
Sodium hydroxide	5%	65
Sodium hydroxide	25%	65
Sodium hydroxide	40%	65
Sodium hypochlorite	1-20%	50
Iron(III)chloride	All	90
Sodium chloride	All	90
Iron(III)sulphate	All	90
CuSO ₄ /H ₂ SO ₄ Electrolyte	20%	65
Ethyl alcohol	15%	50
Ethyl alcohol	45%	50
Carbon tetrachloride	100%	25
Phenol	100%	Not recommended at any temperature
Styrene	100%	Not recommended at any temperature
Acetone	100%	Not recommended at any temperature
Gasoline unleaded, non-containing methanol	100%	50

CIECH Sarzyna S.A.

ul. Chemików 1
 37-310 Nowa Sarzyna
 tel. (+48 17) 24 07 111
 faks (+48 17) 24 07 122
 sarzyna@ciechgroup.com
 www.ciechgroup.com

REGON: 000042352

NIP: 8160001828

Kapitał zakładowy:

84 900 000,00 zł (wplacony w całości)

Rejestr przedsiębiorców:

Sąd Rejonowy w Rzeszowie, XII Wydział
 Gospodarczy Krajowego Rejestru Sądowego
 KRS: 0000103271